



INDIPRIM #508 (GALLON)**Surface Preparation (The following steps are recommended for product performance.):**

- All surfaces must be clean, free of dust, chalk, oil, grease, wax, polish, mold, and mildew, loose peeling paint, rust and all other foreign substances.
- If washing is necessary, use a non-soapy detergent or a TSP substitute, rinse well and allow to dry.
- Unpainted, exterior wood exposed to sun and/or moisture longer than 2-4 weeks must be cleaned and sanded before priming.
- Glossy surface: For maximum adhesion, scuff sand the surface thoroughly before priming.
- Peeling or Checked Paint: Scrape off loose paint and sand to a smooth surface.
- Mold or Mildew Covered Surfaces: Wash the area with a mildew remover, rinse with water and allow to dry before priming.
- Masonry, Brick, Stucco and Plaster: INDIPRIM #508 Primer may be used on clean, dry, aged masonry surfaces. New masonry must be allowed to cure (dry) at least 30 days before applying INDIPRIM #508 Primer.
- Fire Restoration: It is critical to clean damaged surfaces thoroughly before priming.

Application:

- Eye protection is recommended. For spray applications, a small amount of water (no more than 1/2 pint per gallon) may be added. Do not thin for stainblocking applications. Only apply if surface, air and product temperature are between 50°-90°F (10°-32°C). Stir thoroughly before and occasionally during use.
- Brush – High quality Nylon/Polyester.
- Roller – High quality 3/8-1/2" nap on smooth surfaces or 1/2-3/4" nap on semi-rough or porous surfaces.
- Airless spray - .017 - .021 tip/60 mesh filter.
- Prime the entire surface to ensure a uniform appearance of the top coat.
- Stainblocking: INDIPRIM #508 Primer is formulated to block light or medium stains.
- Tinting: INDIPRIM #508 Primer may be tinted with up to 2 ounces of universal colorant per gallon.
- Coverage: 300-400 sq. ft. (27.87 – 37 m²) per gallon depending on application method and surface porosity.
- Dry time @ 77°F (25°C) / 50% RH: Touch in 30 minutes. Paint in 1 hour.

Clean-Up & Disposal:

- Clean equipment and paint spatters with warm, soapy water.
- Do not dispose of this product down a drain. Please consider donating any unused product. For recycling or disposal information contact your local household refuse collection service.
- If spilled, contain material and remove with an inert absorbent. Dispose of contaminated absorbent, container and unused product in accordance with all current federal, state and local regulations.
- USE ONLY WITH ADEQUATE VENTILATION



INDICOTE® (GALLON OR QUART)**Surface preparation:**

Thoroughly clean the surface and allow to dry. Remove all dirt, dust, chalk, rust, grease, wax and mildew. Previously painted surfaces (including painted metal siding): Scrape off loose and peeling paint, sand smooth, then spot prime. Thoroughly remove chalk by vigorous washing then rinse. Remove gloss from shiny surfaces. Countersink nails and apply an oil-based metal primer to exposed nail heads. Caulk cracks and joints. Metal: New galvanized surfaces should be allowed to age 6 months before painting.

Application:

Stir paint thoroughly. Apply only when paint surface and air temperatures are 35-90 °F (2-32 °C) during application and drying time. Do not paint if temperatures are expected to be below 35 °F (2 °C) within 48 hours of application or when heavy dew or precipitation is expected in the next 12 hours. Brush: Use a premium-quality nylon/polyester brush. Roller: 3/8-1/2 inch nap, premium-quality synthetic cover. Airless spray: 2000 PSI, 0.015-0.021" tip. These recommendations are a starting point only. Due to variability in sprayers, we recommend testing your spray pattern and flow before proceeding. If spraying large surfaces, be sure to back-brush or roll immediately after spraying.

Cleanup, storage and disposal:

Clean up with warm, soapy water. Do not freeze. Keep container closed when not in use. Do not transfer contents to other containers for storage or disposal. In case of spills, absorb with inert material such as sand or kitty litter. Dispose of empty container or unused portion in accordance with local, state and federal regulations.

For airless spray:

Thin with up to 8 oz. water per gallon (236 mL per 3.78 L) — only if paint is too thick for sprayer.

Dry to touch: 1 hour at 77 °F (25 °C) and 50% relative humidity. Recoat: 4 hours at 35-45 °F (2-7 °C)